

CPI

Cellupaper For Industry

Quality Control Department

Pulp and Paper Laboratory



سليوبير
لصناعة الورق (سي.بي.اي)

PAPER DATA SHEET

Test Type	Test Method	Unit	Tolerance	HP FLUTING			TESTLINER				Super Cellu
Grammage	T-410	g/m ²	± 5%	112	125	150	125	140	150	170	150
Burst	T-807	kPa	± 5%	2.8	3.0	3.3	3.2	3.5	3.6	3.9	4.0
COBB 60 Sec		g/m ²		70-100	70-100	70-100	30-40	30-40	30-40	30-40	30-40
Thickness	T-411	micron	± 5%	180	190	220	200	210	220	235	230
R.C.T (MD)	T-822	KgF	± 5%	15	17	22	18	20	25	28	27
R.C.T (CD)	T-822	KgF	± 5%	20	22	31	26	31	35	39	37
S.C.T (CD)	T-826	kN/m	± 5%	2.0	2.1	2.3	2.2	2.3	2.5	2.8	3.2
Tensile Strength (MD) (25 mm)	T-494	KgF	± 5%	13.3	14.5	18	14.5	16	20	22	22
Tensile Strength (CD) (25 mm)	T-494	KgF	± 5%	5.7	6.2	8.0	6.2	7.0	9.0	10.0	10.0
C.M.T (MD)	ISO 7263	KgF	± 5%	21	25	27	0	0	0	0	0
C.M.T (CD)	ISO 7263	KgF	± 5%	13	14	16	0	0	0	0	0
Moisture Content	T-412	%	± 5%	7	7	7	7	7	7	7	7

