



**Cellupaper For Industry**  
**Quality Control Department**  
**Pulp and Paper Laboratory**



**PAPER DATA SHEET**

Test Type	Test Method	Unit	Cellukraft					
Grammage	T-410	g/m <sup>2</sup>	125		135		150	
			Target	Min	Target	Min	Target	Min
Burst	T-807	kPa	380	350	450	420	480	460
S.C.T (CD)	T-826	kN/m	3.2	3.1	3.4	3.2	3.6	3.5
C.M.T (MD)	T-809	N	380	360	440	420	470	450
Thickness	T-411	μ	180	170	190	180	230	220
Gurley	ISO 5636-5	Sec	60	50	60	50	60	50
Cobb 60 Sec	T-441	g/m <sup>2</sup>	20-30		20-30		20-30	
Moisture Content	T-412	%	8	6	8	6	8	6

Only the products that are identified as such on this document are FSC™ Certified





**Cellupaper For Industry**  
**Quality Control Department**  
**Pulp and Paper Laboratory**



**PAPER DATA SHEET**

Test Type	Test Method	Unit	Semi-Chemical Fluting R	
Grammage	T-410	g/m <sup>2</sup>	150	
			Target	Minimum
Burst	T-403	kPa	450	400
S.C.T (CD)	T-826	kN/m	3.5	3.1
C.M.T (MD)	T-494	N	450	400
Thickness	T-411	μ	230	210
Gurley	T-460	Sec	55	45
Cobb 60 Sec	T-441	g/m <sup>2</sup>	20-30	20-30
Moisture Content	T-412	%	8	6

Only the products that are identified as such on this document are FSC™ Certified





**Cellupaper For Industry**  
**Quality Control Department**  
**Pulp and Paper Laboratory**



**PAPER DATA SHEET**

Test Type	Test Method	Unit	CelluDual VHP			
			125		150	
			Target	Min	Target	Min
Grammage	T-410	g/m <sup>2</sup>				
Burst	T-403	Kpa	370	330	400	370
S.C.T (CD)	T-826	kN/m	3.0	2.5	3.3	3.0
C.M.T (MD)	T-809	N	400	350	430	400
Thickness	T-411	μ	200	180	240	220
Cobb 60 Sec	T-441	g/m <sup>2</sup>	20-30		20-30	
Moisture Content	T-412	%	8	6	8	6

**Only the products that are identified as such on this document are FSC™ Certified**

